
MB 1.1 STEEL



MB 1.1 DESCRIPTION

Highest temperature service novolac vinyl ester with a non-silica graphite filling for the finish coat.



COMMON AREAS OF USE

• As a lining for fluosilicic and HF when nonsilica filled materials are preferred

MB 1.1 DETAILS

Surface Preparation	SSPC-SP10 / NACE 2 / 3.0-mil minimum anchor profile		
Prime Coat (Stripe)	Series <u>1407</u> Vinester*	4-6 mils DFT	275 sq ft / gal
First Coat	Series <u>1438</u> Vinester	20 mils DFT	65 sq ft /gal
Finish Coat	Series <u>1448</u> Vinester	25 mils DFT	55 sq ft /gal
		50 mils DFT	

*Do not use Series 1407 in wet or dry services of >180°F (82°C) or 200°F (93°C) spikes. Preference is direct-to-metal. Note: Coverage rates are theoretical (no loss). Reference Tnemec data sheets, application guides and construction details for more information.

Published technical data, instructions and pricing are subject to change without notice. Contact your Themee technical representative for current technical data, instructions and pricing. Warranty information: The service life of Themee's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Themee Product Data Sheets at themee.com or contact your Themee technical representative. The service life of Themee's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Themee Product Data Sheets at themee.com or contact your Themee technical representative. The service life of Themee's coatings will vary.