

## RECOMMENDED USE DEFINITIONS

### IMMERSION SERVICE (Most Severe) – IS

Suitable for continuous contact with chemical exposure up to specified temperature.

### CARGO/TEMPORARY IMMERSION – CI

Suitable for 60 day continuous contact with chemical exposure up to specified temperature. Coating will show no effect except slight softening or discoloration, possibly permanent, after 60 days or less continuous immersion. When used in transport or hauling conditions, the vessel must be completely drained to prevent puddling that would constitute continuous immersion.

### SECONDARY CONTAINMENT – SC

Suitable for continuous contact up to 72 hours with chemical exposure or vapors. The coating will show no effects, except slight softening or discoloration, after 72 hours exposure to chemical or vapors. Data references the chemical resistance of the coating. System recommendation may include mat- or aggregate-reinforcement depending on substrate and/or exposure conditions.

### FREQUENT CONTACT – FC

Suitable for frequent splash or up to 72 hours exposure to concentrated vapors. The coating will show no effects except slight softening or discoloration, possibly permanent, after eight hours continuous immersion in the liquid chemical or 72 hours exposure to the vapor.

### OCCASIONAL CONTACT (Least Severe) – OC

Suitable for occasional splash and spillage or occasional exposure to concentrated vapors. The coating shows no effects, except slight softening or discoloration, following short exposure to splash or spillage which evaporates, is hosed off, or dried overnight or, 24 hours exposure to vapor.

### NOT EVALUATED - NE

This chemical has not been evaluated for the listed chemical. Please contact Tnemec Technical Services for more information.

### NOT RECOMMENDED - NR

This product is not recommended for the listed exposure.

## CHEMICAL REFERENCES

The following references may be included in the chemical resistance guide listed below.

- 1 Product is NOT suitable for direct or indirect food contact. Intended Use and temperature information relates to product's performance capabilities only.
- 2 Product is suitable for direct or indirect food contact. Reference product data sheet for more information.
- 3 Service requires elevated temperature post cure (PC) of lining. Reference the product data sheet and application guide for more information.
- 4 System requires use of carbon veil. Reference the product data sheet and application guide for more information.
- 5 System requires use of glass surfacing veil. Reference the product data sheet and application guide for more information.

## IMPORTANT NOTES

The term "chemicals" is used broadly in this guide and can refer to various constituents including, but not limited to, acids, fatty acids, food and beverage materials, finished and unrefined hydrocarbons, as well as individual chemicals and chemical blends. Unless otherwise referenced, the concentrations listed are aqueous solutions of the chemicals.

Temperature can have a significant effect on a coating's chemical resistance. Prior to coating selection, due care should be taken to determine the service temperature of stored chemicals, elevated temperature caused by natural environmental conditions (i.e. radiant heat from sun, weather), and temperature fluctuations during service (i.e. loading of cargo, service cycling).

Chemical mixtures and alternating chemical storage can aggressively degrade a coating or lining system. Prior to coating selection and application, the expected chemical exposures and sequence of chemical storage should be discussed with Tnemec Technical Service to ensure the proper coating is selected.

Proper surface preparation is always important to ensure optimum coating performance, but it is even more so for coatings that will undergo chemical exposure. Carefully read product data sheets along with related application guides to determine the required level of surface preparation and surface profile.

Structural designs of tanks, structures, and containment areas can greatly affect coating performance. Sharp angles, channels, edges, corners, pits, voids, defects, rough welds, and other similar conditions present areas that are either difficult to coat or achieve the required film thickness. Avoid skip welds in favor of continuous welds. A stripe coat on these areas, prior to full coating application, can help achieve needed film thickness and prevent premature coating failure. (Reference NACE SP0178-2007 for more information.)

The length of a coating system's service life depends on surface cleanliness and preparation prior to application, proper application procedures, exposure conditions, physical abuse, cleaning techniques, and frequency of inspection, maintenance, and repair. No coating system has an unlimited service life. Regular inspection of the coating system can prolong service life by identifying areas in need of repair. Additionally, regular inspections can determine when the coating system is nearing its end of service and should be completely replaced.

Chemical resistance information is provided for the purpose of establishing a general profile of the coating and was obtained through laboratory testing, field experience, and industry knowledge. Test results were produced in a controlled environment and Tnemec makes no claim that any tests, or published chemical resistance information, accurately represent all environments or correlate to actual field performance. Application, environmental and design factors, chemical temperatures, chemical mixtures, sequence of storage, conditions of service, and cleaning procedures can significantly impact coating performance, so due care must be exercised in the selection and use of the coating. Tnemec disclaims responsibility for product use outside its published information. Contact Tnemec Technical Service to review full project details before the coating or coating system is selected and applied.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
1, 1, 1-Trichloroethane (Trichloroethane)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Acetaldehyde	NR	NR	NR	NR	NR
Acetic Acid					
5%	NR	NR	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	130°F (54°C) - MB-3.0
10%	NR	NR	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	130°F (54°C) - MB-3.0
30%	NR	NR	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	130°F (54°C) - MB-3.0
75%	NR	NR	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Acetic Acid, Glacial	100°F (38°C)	100°F (38°C)	NR	NR	NR
Acetic Anhydride	100°F (38°C)	100°F (38°C)	NR	NR	NR
Acetone	100°F (38°C)	100°F (38°C)	NR	NR	NR
Acetonitrile					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
100%	NR	NR	NR	NR	NR
Acrylic Acid	100°F (38°C)	100°F (38°C)	NR	NR	NR
Acrylonitrile	NR	NR	NR	NR	NR
Activated Carbon (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - SS-3.0	120°F (49°C) - SS-3.0
Adipic Acid (Dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Allyl Chloride	300°F (149°C)	300°F (149°C)	NR	NR	NR
Aluminum Chloride					
25%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Aluminum Hydroxide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	130°F (54°C) - MB-3.1	130°F (54°C) - MB-3.1
Aluminum Nitrate					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - MB-3.0	140°F (60°C) - MB-3.0
Ammonium Bisulfite	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - RS-1.0	140°F (60°C) - RS-1.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Ammonium Carbonate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Ammonium Chloride					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.2	140°F (60°C) - SS-3.2
Ammonium Fluoride (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - RS-7.1	120°F (49°C) - RS-7.1
Ammonium Hydroxide (Aqua Ammonia)					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	120°F (49°C) - MB-3.1	120°F (49°C) - MB-3.1
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NR	NR
Ammonium Lauryl Sulfate					
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Ammonium Nitrate					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
38%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Ammonium Nitrite					
50%	NR	NR	NR	NR	NR
Ammonium Perchlorate (Dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - MB-3.0	140°F (60°C) - MB-3.0
Ammonium Persulfate					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Ammonium Phosphate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Ammonium Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Ammonium Sulfide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Ammonium Sulfite	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Ammonium Thiosulfate					
60%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Amyl Acetate	NR	NR	NR	NR	NR
Aniline	NR	NR	NR	NR	NR
Animal Fats	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Aqua Regia	NR	NR	NR	NR	NR
Aviation Gas	NR	NR	NR	NR	NR
Barium Chloride					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Barium Hydroxide					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	130°F (54°C) - MB-3.1	140°F (60°C) - MB-3.1
Barium Nitrate	120°F (49°C)	120°F (49°C)	NR	NR	NR
Barium Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Barium Sulfide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Barley (malt) (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Beer (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	110°F (43°C) - SS-3.0	110°F (43°C) - SS-3.0
Beet (liquor) (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	140°F (60°C) - SS-3.1
Benzene	NR	NR	NR	NR	NR
Benzene Sulfonic Acid	120°F (49°C)	120°F (49°C)	NR	NR	NR
Benzoic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Benzoyl Chloride	120°F (49°C)	120°F (49°C)	NR	NR	NR
Benzyl Alcohol	NR	NR	NR	NR	NR
Benzyl Chloride	120°F (49°C)	120°F (49°C)	NR	NR	NR
Biodiesel (<2% FAME)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Black Liquor (3) (5)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - RS-7.1	140°F (60°C) - RS-7.1
Boric Acid					
5%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Brake Fluid (DOT 3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Brine chlorinated (ph 5-9) <12,000 ppm chlorides	NR	NR	NR	NR	NR
Brown Stock	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Butyl Acrylate	100°F (38°C)	100°F (38°C)	NR	NR	NR
Butyl Amine	NR	NR	NR	NR	NR
Butyric Acid	140°F (60°C)	140°F (60°C)	NR	NR	NR
Cadmium Bromide					
10%	NR	NR	NR	NR	NR
Cadmium Chloride	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	140°F (60°C) - MB-2.1	140°F (60°C) - MB-2.1
Cadmium Plating (Cyanide) (3) (4)	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	140°F (60°C) - RS-8.1	140°F (60°C) - RS-8.1
Calcium Bisulfate	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	140°F (60°C) - MB-2.1	140°F (60°C) - MB-2.1
Calcium Bromide	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	140°F (60°C) - MB-2.1	140°F (60°C) - MB-2.1
Calcium Carbonate (Limestone Slurry)	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	NE	NE
Calcium Chloride	400°F (204°C)	400°F (204°C)	300°F (149°C) - RS-1.1	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Calcium Hydroxide (Lime Slurry)					
30%	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	NE	NE
100%	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	NE	NE
Calcium Hypochlorite					
5%	120°F (49°C)	120°F (49°C)	NR	NR	NR
Calcium Nitrate	400°F (204°C)	400°F (204°C)	300°F (149°C) - RS-2.1	140°F (60°C) - MB-2.1	140°F (60°C) - MB-2.1

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Calcium Nitrite	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-2.1	120°F (49°C) - MB-1.1	120°F (49°C) - MB-1.1
Calcium Sulfate	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	140°F (60°C) - MB-2.1	140°F (60°C) - MB-2.1
Calcium Sulfite	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-2.1	120°F (49°C) - MB-2.1	120°F (49°C) - MB-2.1
Caprolactam	120°F (49°C)	120°F (49°C)	NR	NR	NR
Caramel (2)	400°F (204°C)	400°F (204°C)	400°F (204°C) - RS-1.1	NR	NR
Carbon Disulfide	100°F (38°C)	100°F (38°C)	NE	NE	NE
Carbon Tetrachloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Cashew Nut Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.0	140°F (60°C) - SS-3.0
Castor Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.0	150°F (66°C) - SS-3.0
Chlorinated Pulp	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	PC	PC
Chlorine Dioxide (gas)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Chlorine Dioxide (Wet, Saturated)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Chlorine Dioxide Generator	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Chlorobenzene	120°F (49°C)	120°F (49°C)	NR	NR	NR
Chloroform	NR	NR	NR	NR	NR
Chlorosulfonic Acid	NR	NR	NR	NR	NR
Chromic Acid					
10% (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	110°F (43°C) - SS-3.1	110°F (43°C) - SS-3.1
20% (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	110°F (43°C) - SS-3.1	110°F (43°C) - SS-3.1
25%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Citric Acid					
50% <sup>2</sup>	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Coal (high and low sulfur)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Cobalt Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Cobalt Citrate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Coconut Oil (refined) (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Cod Liver Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - SS-3.0	100°F (38°C) - SS-3.0
Cola (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - SS-3.0	120°F (49°C) - SS-3.0
Copper (I) Chloride (Cuprous Chloride)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Copper Acetate					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Copper Sulfate					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Copper Sulfate (dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Corn Mash Solution (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Corn Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Corn Starch (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Corn Syrup (white) (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Cottonseed Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Cresylic Acid (Cresol)	NR	NR	NR	NR	NR
Crude Oil (Sour)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	170°F (77°C) - SS-3.1	170°F (77°C) - SS-3.1
Crude Oil (Sweet)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	170°F (77°C) - SS-3.1	170°F (77°C) - SS-3.1

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Cumene	NR	NR	NR	NR	NR
Cumene Hydroperoxide	NE	NE	NE	NE	NE
Cyclohexane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Cyclohexanol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Cyclohexanone	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Cyclohexylamine	NR	NR	NR	NR	NR
Dextrose (2) (d-glucose)	130°F (54°C)	130°F (54°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.0	130°F (54°C) - SS-3.0
Diacetone Alcohol	NR	NR	NR	NR	NR
Dichloroacetic Acid					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Diethanolamine	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Diethylene Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Diethylene Glycol Monobutyl Ether (Butyl "Carbitol")	NE	NE	NE	NE	NE
Diethylene Glycol Monobutyl Ether Acetate (Butyl "Carbitol" Acetate)	NE	NE	NE	NE	NE
Diethylenetriamine	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Dimethyl Formamide	140°F (60°C)	140°F (60°C)	NR	NR	NR
Diocetyl Phthalate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Dipropylene Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Dodecyl Alcohol (Lauryl Alcohol)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Ethanol (2) (Denatured Alcohol, Ethyl Alcohol)	NR	NR	NR	NR	
50% <sup>2</sup>	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - SS-3.0	100°F (38°C) - SS-3.0
95% <sup>2</sup>	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
100% <sup>2</sup>	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Ethanolamine	NE	NE	NE	NE	NE
Ethyl Acetate	NR	NR	NR	NR	NR
Ethyl Benzene	NR	NR	NR	NR	NR
Ethylamine					
20%	NR	NR	NR	NR	NR
Ethylene Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Ethylene Glycol Monobutyl Ether (Butyl "Cellosolve")	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Ethylene Glycol Monobutyl Ether Acetate (Butyl "Cellosolve" Acetate)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Ethylenediamine					
20%	NR	NR	NR	NR	NR
Fatty Acids (Greater than C6)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Ferric Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Ferric Nitrate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Ferric Sulfate					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
60%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Ferrous Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Flue Gas (dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	225°F (107°C) - MB-3.0	225°F (107°C) - MB-3.0
Flue Gas (wet)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Fluoboric Acid	NE	NE	NE	NE	NE
Fluorosilicic Acid (Hydrofluorosilicic Acid)					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NR	NR

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Formaldehyde					
37%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Formic Acid					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
25%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	120°F (49°C) - MB-3.0
Fructose (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.0	140°F (60°C) - SS-3.0
Furan	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Furfural					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Furfuryl Alcohol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Gasoline (Unleaded)	NR	NR	NR	NR	NR
Glucose (2) (3) (l-glucose)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.0	140°F (60°C) - SS-3.0
Glycerin	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Glycolic Acid					
70%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Gold Plating Solution	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Grape Juice (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.0	130°F (54°C) - SS-3.0
Grapefruit Juice (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.0	130°F (54°C) - SS-3.0
Green Liquor (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Guar Gum (1)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Hand Cleaner (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	110°F (43°C) - SS-3.0	110°F (43°C) - SS-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Heptane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Hexane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Hexanol	NR	NR	NR	NR	NR
Hydraulic Fluid (Hydraulic Oil)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Hydrobromic Acid					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
48%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Hydrochloric Acid					
5%	120°F (49°C)	120°F (49°C)	NE	NE	NE
10%	120°F (49°C)	120°F (49°C)	NE	NE	NE
15%	120°F (49°C)	120°F (49°C)	NE	NE	NE
20%	120°F (49°C)	120°F (49°C)	NE	NE	NE
28%	120°F (49°C)	120°F (49°C)	NE	NE	NE
33%	100°F (38°C)	100°F (38°C)	NE	NE	NE
37%	100°F (38°C)	100°F (38°C)	NE	NE	NE
Hydrofluoric Acid					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NE	NE
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NE	NE
Hydrofluoroboric Acid					
62%	100°F (38°C)	100°F (38°C)	NR	NR	NR
Hydrogen Peroxide					
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Hydrogen Sulfide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Iodine					
5%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Isobutyl Acetate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Isobutyl Alcohol	120°F (49°C)	120°F (49°C)	NR	NR	NR
Isopropyl Alcohol (Isopropanol)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Jet A Fuel	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
JP-4 Aviation Fuel	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
JP-5 Aviation Fuel	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Kaolin	NR	NR	NR	NR	NR
Kerosene	300°F (149°C)	300°F (149°C)	NE	NE	NE
Lactic Acid					
10% (2)(3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
85% (2)(3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
100% (2)(3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Lauryl Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Lead Acetate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Levulinic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Linseed Oil (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.0	140°F (60°C) - SS-3.0
Lithium Bromide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Lithium Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Lithium Hydroxide (saturated) (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	130°F (54°C) - RS-7.1	130°F (54°C) - RS-7.1
LPG (gas)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Lubricating Oil (SAE 5W-40, et al) (Motor Oil)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Magnesium Bisulfite	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Magnesium Chloride					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Magnesium Hydroxide					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	130°F (54°C) - MB-3.0
Magnesium Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Maleic Acid					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Maleic Anhydride	120°F (49°C)	120°F (49°C)	NR	NR	NR
Malic Acid	100°F (38°C)	100°F (38°C)	NR	NR	NR
Mercuric Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Mercury	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Methacrylic Acid	NR	NR	NR	NR	NR
Methane Gas	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Methanol (Methyl Alcohol)	100°F (38°C)	100°F (38°C)	NE	NE	NE
Methyl Acetate	NR	NR	NR	NR	NR
Methyl Acrylate	NR	NR	NR	NR	NR
Methyl Amyl Ketone	NR	NR	NR	NR	NR
Methyl Ethyl Ketone	NR	NR	NR	NR	NR
Methyl Isobutyl Chloride	NR	NR	NR	NR	NR
Methyl Isobutyl Ketone	NR	NR	NR	NR	NR
Methyl Methacrylate	NR	NR	NR	NR	NR
Methyl Propyl Ketone	NR	NR	NR	NR	NR
Methyl tert-Butyl Ether (MTBE)	NR	NR	NR	NR	NR
Methylene Chloride	NR	NR	NR	NR	NR
Methylstyrene (alpha)	NR	NR	NR	NR	NR
Milk (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.0	130°F (54°C) - SS-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Milk Whey (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.0	130°F (54°C) - SS-3.0
Mineral Oil	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Mineral Spirits	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Molasses (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Morpholine	NE	NE	NE	NE	NE
Mustard (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - SS-3.0	120°F (49°C) - SS-3.0
Naphtha	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Naphthalene	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Naphthenic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
n-Butyl Acetate (Butyl Acetate)	120°F (49°C)	120°F (49°C)	NR	NR	NR
n-Butyl Alcohol (1-Butanol) (Butanol (Normal))	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
n-Decyl Alcohol (Decyl Alcohol (1-Decanol))	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Nickel Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Nitric Acid					
5%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
25%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
60%	NR	NR	NR	NR	NR
70%	NR	NR	NR	NR	NR
Nitrobenzene	NR	NR	NR	NR	NR
n-Methyl-2-Pyrrolidone	NE	NE	NE	NE	NE

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
n-Octyl Alcohol (Octanol)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
n-Propyl Alcohol (Propyl Alcohol)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Oleic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Olive Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Oxalic Acid					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Ozone <2 ppm	NR	NR	NR	NR	NR
Palm Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.1	130°F (54°C) - SS-3.1
Pentane	NR	NR	300°F (149°C) - RS-1.0	NR	NR
Perchloric Acid					
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Perchloroethylene (Tetrachloroethylene)	NR	NR	NR	NR	NR
Petroleum Ether	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Phosphoric Acid					
5%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
25%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
43%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
85%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
115%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Phosphorous	NE	NE	NE	NE	NE
Phosphorous Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Phthalic Acid (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Picric Acid (conc)	NR	NR	NR	NR	NR
Pine Oil	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Polyethylene Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - MB-5.0	150°F (66°C) - MB-5.0
Polypropylene	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Polystyrene	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Polytetrafluoroethane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Polyvinyl Acetate Emulsion	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Polyvinyl Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Potash Ore	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Potassium Acetate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Potassium Bromide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Potassium Carbonate					
25% (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
50% (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Potassium Chlorate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Chloride	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Cyanide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Ferricyanide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Fluoride (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Potassium Hydroxide					

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
50% (3) (5)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	130°F (54°C) - RS-7.1	130°F (54°C) - RS-7.1
Potassium Iodide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Potassium Nitrate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Permanganate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Persulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Potassium Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Propane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Propanol	NR	NR	NR	NR	NR
Propionic Acid					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
50%	300°F (149°C)	130°F (54°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
100%	100°F (38°C)	100°F (38°C)	NR	NR	NR
Proponal (fumes)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Propylene Glycol	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Pulpmill (Black Liquor) (3) (5)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - RS-7.1	140°F (60°C) - RS-7.1
Pulpmill (Green Liquor) (3) (5)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - RS-7.1	140°F (60°C) - RS-7.1
Pulpmill (White Liquor) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - MB-3.1	140°F (60°C) - MB-3.1
Pyridine					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Silver Nitrate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Acetate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Aluminate (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - MB-7.1	140°F (60°C) - MB-7.1

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Sodium Bisulfate					
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Bisulfite					
38%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Borate (Borax)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Bromide (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Carbonate (sat'd) (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Sodium Carbonate (slurry) (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Sodium Chlorate					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Chloride (sat'd) (Brine, Water (Sea), Salt Brine)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Sodium Chlorite (>6 pH)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Sodium Chromate					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Cyanide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Dichromate (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Fluoride (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - RS-7.1	140°F (60°C) - RS-7.1
Sodium Formate					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Sodium Hydrosulfide					
45%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Hydrosulfite					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Sodium Hydroxide (Caustic Soda)					
50% (3) (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Sodium Hypochlorite (Bleach)					
6%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	120°F (49°C) - MB-3.1	120°F (49°C) - MB-3.1
13%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NR	NR
15%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	NR	NR
Sodium Lauryl Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Nitrate					
40%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Nitrate (dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Oxalate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Phosphate					
10% (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Sodium Silicate (4)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	150°F (66°C) - RS-7.1	150°F (66°C) - RS-7.1
Sodium Sulfate					
6%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Sodium Sulfide (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Sulfite	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Sodium Thiosulfate					
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Soy Sauce (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Soybean Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Soybean Oil (ESO) (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - SS-3.1	120°F (49°C) - SS-3.1
Spearmint Oil (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - SS-3.1	100°F (38°C) - SS-3.1
Stannic Chloride (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Stannous Chloride (all)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Stearic Acid (conc)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Stoddard Solvent	NR	NR	NR	NR	NR
Styrene	100°F (38°C)	100°F (38°C)	NR	NR	NR
Sugars (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Sulfite Liquor (paper industry)	PC	PC	PC	PC	PC
Sulfur Dioxide (dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	225°F (107°C) - MB-3.0	225°F (107°C) - MB-3.0
Sulfur Dioxide (wet)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Sulfuric Acid (Sulphuric Acid)					
5%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
30%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
70%	NR	NR	NR	NR	NR
98%	NR	NR	NR	NR	NR
Sulfurous Acid					
10%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Tall Oil	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0
Tannic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Tartaric Acid (2)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Tetrahydrofuran	NR	NR	NR	NR	NR
Toluenesulfonic Acid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Tomato Sauce (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.2	150°F (66°C) - SS-3.2
Transmission Fluid	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Trichloroethylene (Vinyl Trichloride)	NR	NR	NR	NR	NR
Trichlorofluoroethane	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NR	NR
Triethanolamine (TEA)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	100°F (38°C) - MB-3.0	100°F (38°C) - MB-3.0
Triethylamine	100°F (38°C)	100°F (38°C)	NR	NR	NR
Triethylenetetramine	NR	NR	NR	NR	NR
Trisodium Phosphate (Sodium Phosphate (Tribasic))					
20%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - SS-3.1	130°F (54°C) - SS-3.1
Turpentine	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Urea					
50%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Urea Ammonium Nitrate					
32%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	110°F (43°C) - MB-3.0	110°F (43°C) - MB-3.0
Vanillin (Black Liquor) (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - SS-3.0	120°F (49°C) - SS-3.0
Vegetable Oil (1)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	NE	NE
Vinegar (2) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	150°F (66°C) - SS-3.1	150°F (66°C) - SS-3.1
Water (deionized, non-potable) (1) (3) (Water (Demineralized, Non-potable))	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
Water (distilled, non-potable) (1) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.

# PROPOLYMER™ | SERIES 1430

Chemical	Intended Use (Maximum Temperature Listed)				
	Occasional Contact	Frequent Contact	Secondary Containment	Cargo Immersion	Immersion Service
Water (fresh, non-potable) (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - SS-3.1	140°F (60°C) - SS-3.1
White Liquor (3)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.1	140°F (60°C) - MB-3.1	140°F (60°C) - MB-3.1
Xylene	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	80°F (27°C) - MB-3.0	80°F (27°C) - MB-3.0
Zinc Bromide	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Zinc Chloride					
40%	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	120°F (49°C) - MB-3.0	120°F (49°C) - MB-3.0
Zinc Phosphate (dry)	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	140°F (60°C) - MB-3.0	140°F (60°C) - MB-3.0
Zinc Sulfate	300°F (149°C)	300°F (149°C)	300°F (149°C) - RS-1.0	130°F (54°C) - MB-3.0	130°F (54°C) - MB-3.0

IMPORTANT: Definitions for the terms and acronyms used in this guide to describe the recommended exposures, along with other important information, can be found on the cover page of this guide or by contacting Tnemec Technical Service. Coatings should not be applied in a chemical exposure environment until the user has thoroughly read and understood the product information and full project details have been discussed with Tnemec Technical Service.