

URETHANE ACCELERATOR

SERIES 44-710

PRODUCT PROFILE

GENERIC DESCRIPTION

Amine and Tin Catalysts

COMMON USAGE

Special additive for most Tnemec urethane coatings affording low temperature application and accelerated cure for rapid handling and recoat situations.

COLOR

Clear Yellow

SPECIAL QUALIFICATIONS

Series 44-710 Urethane Accelerator is ANSI/NSF Std. 61 certified as a component of Series 1, 91-H₂O, and 94-H₂O when used in potable water applications.

TECHNICAL DATA

VOLUME SOLIDS

5.7 ± 1%

**CURING TIME POT LIFE
MODIFICATIONS**

The following table provides data on the approximate curing and pot life times for various Tnemec urethane coatings, when Series 44-710 Accelerator has been added. See Mixing section for amount of accelerator and special instructions for mixing. **Caution:** With the use of Series 44-710 Urethane Accelerator a slight change in gloss may occur in cured finishes.

Approximate Hours Curing Time / Pot Life at 50% R.H.

PRODUCT SERIES NUMBER	DRY-TO-TOUCH 35°-75°F 2°-24°C	DRY-TO-HANDLE					DRY-TO-RECOAT					POT LIFE				
		35°F 2°C	45°F 7°C	55°F 13°C	65°F 18°C	75°F 24°C	35°F 2°C	45°F 7°C	55°F 13°C	65°F 18°C	75°F 24°C	35°F 2°C	45°F 7°C	55°F 13°C	65°F 18°C	75°F 24°C
1 / 394 [†]	¼-1½	2¼	1½	1	¾	½	30	24	20	16	16	8	6½	5	2½	2½
73	½-¾	12	6	4	3	2	20	12	8	7	5	2	2	1½	1	2
90-97	¼	¾	½	½	½	¼	4	4	3	3	2	2	2	2	2	2
91-H ₂ O	¼	¾	½	½	½	¼	4	4	3	3	2	2	2	2	2	2
90G-1K97 / 94-H ₂ O/93-H ₂ O	½	1½	1	1	1	½	8	7	6	5	4	4	4	4	4	4
700 / 1070 / 1078 (V) [‡]	¼-½	8	4	2½	-	-	10	5	4½	-	-	1	1	1	-	-
701 / 1071 (V) [‡]	¼-½	12	10	7	-	-	16	11	12	-	-	2¼	2	2	-	-
1072 [‡]	1-2	15	14	9	-	-	24	24	10	-	-	2¼	2	2	-	-

[†]Values listed are for use with recommended topcoats. Dry to recoat times with itself are: 8 hours at 35°F (2°C), 5 hours at 45°F (7°C), 2 1/2 hours at 55°F (13°C), 2 hours at 65°F (18°C) and 1 3/4 hours at 75°F (24°C). Curing time varies with surface temperature, air movement, humidity and film thickness.

[‡]**Note:** Due to shortened pot life, 44-710 is not recommended for use above 60°F (16°C) in fluoropolymer products.

VOLATILE ORGANIC COMPOUNDS

SERIES	THINNER	UNTHINNED + 44-710	THINNED MAXIMUM + 44-710
1 / 394		2.90 lbs/gallon (347 g/L)	-
	No. 2 / No. 3		3.30 lbs/gallon (395 g/L)
	No. 49		2.90 lbs/gallon (347 g/L)
73		2.84 lbs/gallon (240 g/L)	-
	No. 39		3.18 lbs/gallon (381 g/L)
	No. 42		3.22 lbs/gallon (386 g/L)
	No. 56		2.89 lbs/gallon (347 g/L)
90-97		2.79 lbs/gallon (334 g/L)	3.20 lbs/gallon (383 g/L)

URETHANE ACCELERATOR | SERIES 44-710

TECHNICAL DATA (CONTINUED)

SERIES	THINNER	UNTHINNED + 44-710	THINNED MAXIMUM + 44-710
91-H ₂ O		2.77 lbs/gallon (332 g/L)	3.18 lbs/gallon (381 g/L)
94-H ₂ O		1.06 lbs/gallon (334 g/L)	–
	No. 3		1.82 lbs/gallon (218 g/L)
	No. 49		1.06 lbs/gallon (127 g/L)
700 / 1070		3.05 lbs/gallon (365 g/L)	–
	No. 39		3.20 lbs/gallon (383 g/L)
701 / 1071		2.97 lbs/gallon (356 g/L)	–
	No. 39		3.13 lbs/gallon (375 g/L)
	No. 56		2.99 lbs/gallon (358 g/L)
1072		2.94 lbs/gallon (352 g/L)	–
	No. 39		3.10 lbs/gallon (371 g/L)
	No. 56		2.96 lbs/gallon (355 g/L)
1078		3.50 lbs/gallon (419 g/L)	3.63 lbs/gallon (435 g/L)

PACKAGING

Individual graduated plastic quarts (0.95 L). Also in multiple 4-quart convenience pack.

NET WEIGHT PER GALLON

7.10 ± 0.10 lbs (3.22 ± 0.04 kg)

STORAGE TEMPERATURE

Minimum 20°F (-7°C) Maximum 110°F (43°C)

SHELF LIFE

12 months at recommended storage temperature

FLASH POINT - SETA

102°F (39°C)

HEALTH & SAFETY

Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product. Keep out of the reach of children.

APPLICATION

TIME TO MOISTURE RESISTANCE

PRODUCT SERIES NUMBER	HOURS TO MOISTURE RESISTANCE			
	35°F (2°C)	45°F (7°C)	55°F (13°C)	75°F (24°C)
73	24-40	12-16	7-10	4-6
700/1070/1078 (V) [†]	10	5	21/2	–
701/1071 (V) [†]	17	10	61/2	–
1072 (V) [†]	18	15	8	–

[†]Due to shortened pot life, 44-710 is not recommended for use above 60°F (16°C) in fluoropolymer products.

MIXING

Note: In all mixes, Series 44-710 Accelerator must be added under agitation to avoid lumping, gelling or unpredictable curing. The use of more than the recommended amount of Series 44-710 Accelerator will adversely affect coating performance. Add thinner, if necessary, only after all other components are thoroughly mixed.

Stir thoroughly making sure no pigment remains on the bottom. While maintaining agitation, accurately add four (4) fluid ounces of Series 44-710 Accelerator per gallon yield. For two-component products, Series 44-710 should be added to Part A before mixing with Part B. See product data sheet or label for additional mixing instructions.

URETHANE ACCELERATOR | SERIES 44-710

APPLICATION (CONTINUED)

SURFACE TEMPERATURE

Minimum 35°F (2°C) Maximum: See applicable product data sheet.
The surface should be dry and at least 5°F (3°C) above the dew point.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company Inc. 123 West 23rd Avenue North Kansas City, Missouri 64116 USA +1 816-483-3400 tnemec.com